



# Standard Specification for Pressure Vessel Plates, Carbon Steel, for Intermediate- and Higher-Temperature Service<sup>1</sup>

This standard is issued under the fixed designation A 515/A 515M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification<sup>2</sup> covers carbon-silicon steel plates primarily for intermediate- and higher-temperature service in welded boilers and other pressure vessels.

1.2 Material under this specification is available in three grades having different strength levels as follows:

Grade U.S. [SI]	Tensile Strength, ksi [MPa]
60 [415]	60–80 [415–550]
65 [450]	65–85 [450–585]
70 [485]	70–90 [485–620]

1.3 The maximum thickness of plates is limited only by the capacity of the composition to meet the specified mechanical property requirements; however, current practice normally limits the maximum thickness of plates furnished under this specification as follows:

Grade U.S. [SI]	Maximum Thickness, in. [mm]
60 [415]	8 [200]
65 [450]	8 [200]
70 [485]	8 [200]

1.4 For plates produced from coil, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 20/A 20M apply.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

## 2. Referenced Documents

### 2.1 ASTM Standards:

A 20/A 20M Specification for General Requirements for

## Steel Plates for Pressure Vessels<sup>3</sup>

### 3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A 20/A 20M. These requirements outline the testing and retesting methods and procedures, permissible variations in dimensions, and mass, quality and repair of defects, marking, loading, etc.

3.2 Specification A 20/A 20M also establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

3.3 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. These include:

- 3.3.1 Vacuum treatment,
- 3.3.2 Additional or special tension testing,
- 3.3.3 Impact testing, and
- 3.3.4 Nondestructive examination.

3.4 The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A 20/A 20M.

3.5 Coiled product is excluded from qualification to this specification until it is decoiled, leveled, and cut to length. Plate produced from coil means plate that has been cut to individual lengths from a coiled product and is furnished without heat treatment. The processor decoils, levels, cuts to length, and marks the product. Except as allowed by Section 6 in Specification A 20/A 20M, the processor is responsible for performing and certifying all tests, examinations, repairs, inspections, and operations not intended to affect the properties of the material. For plate produced from coils, the results of the tests performed shall be reported for each qualifying coil. See Note 1.

NOTE 1—Additional requirements regarding plate produced from coil are described in Specification A 20/A 20M.

3.6 If the requirements of this specification are in conflict with the requirements of Specification A 20/A 20M, the requirements of this specification shall prevail.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Sept. 10, 2001. Published September 2001. Originally published as A 515 – 64. Last previous edition A 515/A 515M – 92(1997).

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-515/SA-515M in Section II of that Code.

<sup>3</sup> Annual Book of ASTM Standards, Vol 01.04.

**4. Manufacture**

4.1 *Steelmaking Practice*—The steel shall be killed and made to a coarse austenitic grain size practice.

**5. Heat Treatment**

5.1 Plates 2 in. [50 mm] and under in thickness are normally supplied in the as-rolled condition. The plates may be ordered normalized or stress relieved, or both.

5.2 Plates over 2 in. [50 mm] in thickness shall be normalized.

**6. Chemical Requirements**

6.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S17, Vacuum Carbon-Deoxidized Steel, in Specification A 20/A 20M.

**7. Mechanical Requirements**

7.1 *Tension Test Requirements*—The material as represented by the tension-test specimens shall conform to the requirements shown in Table 2.

**TABLE 1 Chemical Requirements**

Elements	Composition, %		
	Grade 60[Grade 415]	Grade 65[Grade 450]	Grade 70[Grade 485]
Carbon, max <sup>A</sup> :			
1 in. [25 mm] and under	0.24	0.28	0.31
Over 1 to 2 in. [25 to 50 mm], incl	0.27	0.31	0.33
Over 2 to 4 in. [50 to 100 mm], incl	0.29	0.33	0.35
Over 4 to 8 in. [100 to 200 mm], incl	0.31	0.33	0.35
Over 8 in. [200 mm]	0.31	0.33	0.35
Manganese, max:			
Heat analysis	0.90	0.90	1.20
Product analysis	0.98	0.98	1.30
Phosphorus, max <sup>A</sup>	0.035	0.035	0.035
Sulfur, max <sup>A</sup>	0.035	0.035	0.035
Silicon:			
Heat analysis	0.15–0.40	0.15–0.40	0.15–0.40
Product analysis	0.13–0.45	0.13–0.45	0.13–0.45

<sup>A</sup>Applies to both heat and product analyses.

**TABLE 2 Tensile Requirements**

	Grade		
	60 [415]	65 [450]	70 [485]
Tensile strength, ksi [MPa]	60–80 [415–550]	65–85 [450–585]	70–90 [485–620]
Yield strength, min, ksi [MPa]	32 [220]	35 [240]	38 [260]
Elongation in 8 in. [200 mm], min, % <sup>A</sup>	21	19	17
Elongation in 2 in. [50 mm], min, % <sup>A</sup>	25	23	21

<sup>A</sup>See Specification A 20/A20M for elongation adjustment.

**SUPPLEMENTARY REQUIREMENTS**

Supplementary requirements shall not apply unless specified in the order.

A list of standardized supplementary requirements for use at the option of the purchaser are included in Specification A 20/A 20M. Those which are considered suitable for use with this specification are listed below by title.

- S1. Vacuum Treatment,
- S2. Product Analysis,
- S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons,
- S4.1 Additional Tension Test,
- S5. Charpy V-Notch Impact Test,
- S6. Drop-Weight Test,
- S7. High-Temperature Tension Test,
- S8. Ultrasonic Examination in accordance with Specification A 435/A 435M,

- S9. Magnetic Particle Examination,
- S11. Ultrasonic Examination in accordance with Specification A 577/A 577M,
- S12. Ultrasonic Examination in accordance with Specification A 578/A 578M,
- S14. Bend Test, and
- S17. Vacuum Carbon-Deoxidized Steel.

**ADDITIONAL SUPPLEMENTARY REQUIREMENTS**

Also listed below is an additional optional supplementary requirement suitable for this specification:

**S61. Austenitic Grain Size**

S61.1 The material shall have a carburized austenitic grain size of 1 to 5.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*